



# CLEANING ■ SEALING ■ MAINTENANCE

Sealing and maintenance solutions for all types of stone, porcelain, quarry, terracotta and glazed ceramic

## BOILED LINSEED OIL TECHNICAL DATA SHEET REF: 11/5/2

### LTP BOILED LINSEED OIL

Traditional Pre-Polish Sealer for Terracotta.

#### Interior use only

A rich golden coloured oil ideal for protecting and enhancing machine and hand made terracotta. Fills and hardens within the open pores of the terracotta inhibiting the absorption of grime and fluids. Offers good mechanical strength to low fire hand made terracotta.

**IMPORTANT:** Do not let the oil oxidise on the surface of the tile. Remove any surplus, not absorbed into the tiles, within one hour of application using a clean cloth and, if necessary, a little Genuine Turpentine. Experiment on spare tiles to establish the number of coats required to achieve full saturation.

### Directions for use

Apply by brush a coat at a time until the tiles are saturated. Allow at least 12 hours between each coat to ensure that the oil thoroughly oxidises. Most Terracotta will take one or two coats to reach saturation, while others, particularly some of the cruder hand made varieties, may take as many as four, five or even six coats. Leave the final coat to dry for at least 24 hours before polishing with LTP Beeswax or finishing with LTP Ironwax Gloss or Satin.

### Coverage

Medium Porosity Terracotta: 1-2 litres per 10m<sup>2</sup>  
Higher Porosity Terracotta: 3-4 litres per 10m<sup>2</sup>

### Storage information

Store in a cool, dry, frost-free environment.

### Health & Safety

Keep out of the reach of children.

Do not drink.

Keep/Store away from clothing/combustible materials.

Store in a closed container.

Dispose of contents/container to hazardous waste collection point.

May cause minor irritation on skin contact.

May cause minor irritation on eye contact.

Label in Accordance With (EC) No 1272/2008

**DO NOT LEAVE SOILED APPLICATION CLOTHS WHERE THEY MAY CONSTITUTE A FIRE RISK, AS THEY ARE LIABLE TO SPONTANEOUS COMBUSTION.**

Important:

All rags and cloths used should be immediately burnt, or if this is not possible soaked in soapy water before disposing of in a bin. The application cloths should never be crumpled up into a ball.



This information is offered without guarantee. The material should be used so as to take account of the local conditions and the surfaces to be treated. In case of doubt, the product should be tried out in an inconspicuous area.

*for beautiful surfaces we have the solutions...*

LTP, Tone Estate, Milverton Road, Wellington, Somerset, TA21 0AN

T +44 (0) 1823 666213 F +44 (0) 1823 665685 E info@ltp-online.co.uk

[www.ltp-online.co.uk](http://www.ltp-online.co.uk)

January 2013

